



TO: End Buyer, Buyer Mandate

Our Ref: fgmc/83265-D372

**We hereby issue this Offer with given terms and conditions as stated in this offer to confirm our readiness to execute a Sales and Purchase Agreement with end buyer, with the ability to supply the following commodity according to the terms and conditions as below.**

Export Cement Clinker

Origin : China

Min Quantity: 30,000 MT

Max Quantity: large and discuss

Specification : Attached

Price: US \$ pls ask PMT FOB or CIF

Delivery Term: FOB or CIF

Commission: Seller \$0.5 closed and Buyer \$0.5 open

Payment: TT or DLC

Destination Port: any Ports

### **Procedure as below..**

1. Buyer issue Letter of Intent showing all details
2. Factory issue Full Corporate Offer
3. Buyer counter sign FCO and return back to us
4. Buyer issue Bank Instrument
5. Inspection of Goods through Third Party
6. Shipment moves as per agreed schedule
7. Release of payment against Original Shipping Documents

Following clinker spec and test report in pdf

### **Specification**

<b>CEMENT CLINKER TEST RESULT</b>		
<b>Test Period: 2026.01.01 – 2026.03.20</b>		
Item	Unit	Average Result
LSF	–	94.62
Cl-	%	0.029
SiO <sub>2</sub>	%	21
Al <sub>2</sub> O <sub>3</sub>	%	5.83
Fe <sub>2</sub> O <sub>3</sub>	%	4.27
CaO	%	64.2
MgO	%	2.37
S <sub>2</sub> O <sub>3</sub>	%	0.46
K <sub>2</sub> O	%	0.47
Na <sub>2</sub> O	%	0.15
R <sub>2</sub> O	%	0.45
C <sub>3</sub> S	%	52.76
C <sub>2</sub> S	%	20.88
C <sub>3</sub> A	%	8.21
C <sub>4</sub> AF	%	13
C <sub>3</sub> S+C <sub>2</sub> S	%	73.64
CaO/SiO <sub>2</sub>	–	3.06
f-CaO	%	0.6
LOI	%	0.29
Insoluble Residue	%	0.11
80 μm Residue	%	1.77
Specific Surface Area	m <sup>2</sup> /kg	356
Initial Setting	min	134
Final Setting	min	199
Soundness	–	Qualified
3d Flexural	MPa	6.6
28d Flexural	MPa	8.83
3d Compressive	MPa	34.2
28d Compressive	MPa	59.69
Additional Index	–	0.935



---

Pls feel free to contact us for further discussion

Sincerely

Fugo Materials