



Testing Report

Applicant : MATERIAL CO., LTDJob No. : MIN241203528TJ

Address : 8 N
D I, CHINAREport No. : MIN241203528TJ

Product : GRANULATED BLAST FURNACE
SLAGDate Received : December 10,2024

Sample Description : GranuleDate Analyzed : December 12-18,2024

Sample Number :

Item	Unit	Result	Test Standard
Moisture	%	8.85	EN 15167-1: 2016
Al ₂ O ₃	%	18.31	BS EN 196-2: 2013
SiO ₂	%	30.13	BS EN 196-2: 2013
Fe ₂ O ₃	%	0.45	BS EN 196-2: 2013
CaO	%	38.70	BS EN 196-2: 2013
MgO	%	10.47	BS EN 196-2: 2013
Na ₂ O	%	0.35	BS EN 196-2: 2013
Mn ₂ O ₃	%	0.26	BS EN 196-2: 2013
SO ₃	%	0.09	BS EN 196-2: 2013
Cl	%	0.051	BS EN 196-2: 2013
LOI	%	-0.74	BS EN 196-2: 2013
Insoluble Residue	%	0.52	BS EN 196-2: 2013
Sulfide (On the basis of S ²⁻)	%	0.01	BS EN 196-2: 2013
CaO+MgO+Al ₂ O ₃ /SiO ₂	%	2.24	BS EN 196-2: 2013
Glass	%	97.5	GB/T 203-2008

Remark : The testing data and result issued by this report is just for scientific research, teaching, internal quality control, product research and development etc. on reference only in the territory of the People's Republic of China.

*** Blank Below ***

Approved : 杨静Checked : 石磊Edited : 杨俊Issuance Date : December 19 2024

Title Tech Lead



Declaration :

The test report will be only applicable to the samples delivered by clients. Any objection concerning the report should be submitted to the company within one month after the date of issuing report. The test report will be deemed invalid without inspection and test stamp of the test body, without signature of the authorized signatories, or altered. Without the written approval of the company, it is not allowed to copy part of the test report (except copying full report). The sample will not be retained for more than three months.